

LPC 009 POLE - TECHNICAL DATA



STRUCTURE

PAINTING CYCLE

STEEL

ALUMINIUM

Pickling and washing with water demineralized, nanotechnological process, drying at 160°C. Polyester powder primer coat and oven curing at 200°C. Finishing coat with two-component varnish standard gray color (S). RAL colors on request.